



— FILTRATION SAND

Typically, sand is clean, immature sand, dominated by fresh transparent to translucent very light feldspar, but also containing dark pyroxene and other components.

Coarse 0.15 – 2.36mm Approximately 3.79% retained at 2.36mm sieve

Product is available in 20kg or metric tonne (1,000kg) bulk bags.

INDUSTRIAL SANDS LTD. - sieve analysis.

SAND filter sand Coarse

DATE: 9/6/2019

SAMPLE WEIGHT : 200

SIEVE	WGT RET.	% RET.	ACC. % RET.	% PASSING
2.360	7.57	3.79%	3.79%	96.22%
1.180	118.52	59.26%	63.05%	36.96%
0.600	60.03	30.02%	93.06%	6.94%
0.300	9.48	4.74%	97.80%	2.20%
0.150	2.18	1.09%	98.89%	1.11%
PAN	1.62	0.81%	99.70%	0.30%
TOTAL	199.40			

F.MOD: 3.57

